

# RENOBUILD TEXTURING ADDITIVE

# RENOBUILD TEXTURING ADDITIVE Revision: 01/18

# **Description**

Renobuild Texturing Additive is a micronized polymer bead ideal for providing a measure of slip resistance to coatings and sealers.

The rounded shape of Renobuild Texturing Additive provides optimum abrasion resistance without sharp edges, allowing ease of surface cleaning.

The product is also gentle to bare feet, allowing it's use on pool decks & patios etc.

#### **Typical Uses**

In coatings and sealers to impart a lightly textured finish that increases slip resistance. e.g. factory floors, driveways, garages, wet rooms etc.

### **Advantages**

- Non-Toxic
- Controlled particle distribution gives uniform finish.
- Easily incorporated to all coatings and sealers.
- Economical.
- Good balance between slip resistance and ease of cleaning.
- No hard or sharp edges.

## **Procedure**

Renobuild Texturing Additive is added to the mixed coating and stirred thoroughly prior to application.

For specific advice regarding any aspect of this product, please consult our Technical Department at <a href="mailto:renobuild@resbuild.co.uk">renobuild@resbuild.co.uk</a>

#### **Pack Sizes**

Renobuild Texturing Additive is usually supplied in pre-weighed amounts corresponding to the size of the pack it is being added to. Alternatively, Renobuild Texturing Additive can be supplied pre-dispersed; this can be requested when placing an order.

Renobuild Texturing Additive is supplied in 3 grades: **Fine Grade** 

Typically used in Renobuild WB Coating **Standard Grade** 

Typically used in Renobuild SF Coating Course Grade

Typically used in Renobuild Ultracoat

### **Health and Safety**

Please refer to Material Safety Data Sheet for additional information.

Renobuild Texturing Additive shall be applied strictly in accordance with the manufacturer's instructions.

For specific advice regarding any aspect of this product, please consult our Technical Department.

#### **PTV Results**

Product	Dry PTV	Wet PTV
WB Coating	58-60	45-48
SF Coating	48-50	40-42
DPM	49-51	40-43
WB Primer/	50-52	40-42
Sealer		

Test results for other products available on request.

A wet PTV of >36 is considered 'low slip potential'

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Resin Building Products Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).